HTADB/10NL



ISO 22241

IT IMPIEGO

Tubo in gomma long length idoneo per adduzione di UREA al 32.5% (AUS 32).

Normative di riferimento: **ISO 22241.**

• **TEMPERATURA:** -40°C +120°C

STRUTTURA

- **Sottostrato**: liscio in gomma antistatica EPDM nera idonea per passaggio di AD BLUE fino al 32,5%.
- **Rinforzi**: inserzioni di filati sintetici ad alta resistenza.
- **Copertura**: in gomma antistaica (R<1MΩ/m) nera EPDM conduttiva resistente al calore, all'ozono, e agli agenti atmosferici.
- **Superficie**: liscia estrusa.
- **Marcatura**: ad inchiostro "H.T. - BLU - W.P. 10 BAR (150PSI) - AUS 32 ISO 22241 - R<1MΩ/m - LOTTO".

EN APPLICATION

Long length rubber hose suitable for loading of 32.5% UREA (AUS 32).

Standards: **ISO 22241.**

• **TEMPERATURE RANGE:** -40°C +120°C

CONSTRUCTION

- **Tube**: black, smooth, 32,5% AD BLUE resistant antistatic rubber EPDM.
- **Reinforcement**: high strength synthetic textile yarn.
- **Cover**: in black EPDM antistatic rubber (R<1MΩ/m) conductive, heat, ozone and atmospheric agents resistant.
- **Surface**: smooth extruded.
- **Branding**: ink marking "H.T. - BLU - W.P. 10 BAR (150 PSI) - AUS 32 ISO 22241 - R<1MΩ/m - BATCH".

DIAMETRO INTERNO INSIDE DIAMETER		DIAMETRO ESTERNO OUTSIDE DIAMETER		PESO TEORICO WEIGHT		PRESS. ESERCIZIO WORKING PRESSURE		PRESS. SCOPPIO BURST PRESSURE		RAGGIO DI CURVATURA BENDING RADIUS		LUNGHEZZA LENGTH	
mm	inch	mm	inch	kg/mt	lbs/ft	bar	psi	bar	psi	mm	inch	mt	ft
13	1/2"	21	7/8"	0,26	0.17	10	150	30	450	130	5.11	60	200
19	3/4"	27	1 1/16"	0.35	0.23	10	150	30	450	190	7.48	60	196.8
25	1"	35	1.3/8"	0.55	0.37	10	150	30	450	250	9.84	50	164.0

Altri diametri e/o pressioni realizzabili su richiesta - Le caratteristiche e i dati tecnici possono essere modificati senza preavviso.

Other diameters and/or pressures are feasible upon request - The characteristics and technical data could be changed without warning.