

ISOLCORD/20W/FV



IT IMPIEGO

Tubo in gomma cord isolante con fibra di vetro per raffreddamento forni nell'industria siderurgica.

- **TEMPERATURA:** -40°C +120°C

STRUTTURA

- **Sottostrato:** liscio in gomma bianca elettricamente isolante e resistente al calore.
- **Rinforzi:** tessuti sintetici ad alta resistenza.
- **Copertura:** in gomma colorata elettricamente isolante e resistente al calore.
- **Superficie:** in fibra di vetro vulcanizzata e gommata con materiale autoestinguente.

Disponibile su richiesta

ISOLCORD/20W/ZINC con rivestimento in calza di acciaio zincato.

ISOLCORD/20W/INOX con rivestimento in calza di acciaio inox.

EN APPLICATION

Glassfiber insulating softwall rubber hose suitable for cooling of furnaces in steel industries.

- **TEMPERATURE RANGE:** -40°C +120°C

CONSTRUCTION

- **Tube:** white, smooth rubber with insulating properties and heat resistant.
- **Reinforcement:** high strength synthetic textile plies.
- **Cover:** insulating and heat resistant coloured rubber.
- **Surface:** vulcanized glass fibre ply treated with self-extinguishing material.

Available on request

ISOLCORD/20W/ZINC galvanized steel wire braided cover

ISOLCORD/20W/INOX stainless steel wire braided cover.

DIAMETRO INTERNO INSIDE DIAMETER		DIAMETRO ESTERNO OUTSIDE DIAMETER		PESO TEORICO WEIGHT		PRESS. ESERCIZIO WORKING PRESSURE		PRESS. SCOPPIO BURST PRESSURE		LUNGHEZZA LENGTH	
mm	inch	mm	inch	kg/mt	lbs/ft	bar	psi	bar	psi	mt	ft
13	1/2"	25	1"	0.48	0.32	20	300	60	900	30.5/61	100/200
19	3/4"	31	1.7/32"	0.70	0.47	20	300	60	900	30.5/61	100/200
25	1"	37	1.15/32"	0.92	0.61	20	300	60	900	30.5/61	100/200
32	1.1/4"	46	1.13/16"	1.45	0.98	20	300	60	900	30.5/61	100/200
38	1.1/2"	54	2.1/8"	1.80	1.21	20	300	60	900	30.5/61	100/200
51	2"	67	2.41/64"	2.30	1.54	20	300	60	900	30.5/61	100/200
63	2.1/2"	81	3.3/8"	3.43	2.31	20	300	60	900	20	65.5

Altri diametri e/o pressioni realizzabili su richiesta - Le caratteristiche e i dati tecnici possono essere modificati senza preavviso.

Other diameters and/or pressures are feasible upon request - The characteristics and technical data could be changed without warning.